

10/534549

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 May 2004 (21.05.2004)

PCT

(10) International Publication Number
WO 2004/041959 A1

(51) International Patent Classification⁷: C09K 5/10

(21) International Application Number:
PCT/KR2003/002375

(22) International Filing Date:
7 November 2003 (07.11.2003)

(25) Filing Language: Korean

(26) Publication Language: English

(30) Priority Data:
10-2002-0069321
8 November 2002 (08.11.2002) KR

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant and

(72) Inventor: KWON, Dong-Soon [KR/KR]; #414, Bukbyeon-dong, Gimpo-si, 415-030 Gyeonggi-do (KR).

(74) Agent: CHO, Hyeon-Seog; 3rd Fl., Yoonsung Bldg., 628-13, Yeoksam-dong, Kangnam-ku, 135-908 Seoul (KR).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: SOLID MATTER A, LIQUID MATTER B PRODUCED BY USING THE A, LIQUID HEATING MATTER PRODUCED USING THE B AND METHOD FOR PRODUCING THE HEATING MATTER

(57) Abstract: Disclosed are a liquid heating element and a method for production thereof, and more particularly a solid ingredient A, a liquid ingredient B produced from the solid ingredient A, a liquid heating element produced from the liquid ingredient B and a method for producing the liquid heating element. The solid ingredient is produced by heating activated carbon, kaolin, copper sulfide and phosphoric acid (H₃PO₄) to a temperature ranging from 1,000 to 1,200 °C. The liquid ingredient B is produced by mixing the solid ingredient A with silicon powder and distilled water and heating the mixture. The liquid heating element is produced by mixing the liquid ingredient B with ethylene glycol, leaving the mixture and then filtering the mixture. Since the liquid heating element is very stable and generates heat with minimum power consumption, it can be applied to various heat management systems.

WO 2004/041959 A1